TEST REPORT

ULR No: TC-11707241000003106F

Issued To,
M/s Techno Power
163A1/A3 2nd Phase G.I.D.C.
Vapi, Dist. Valsad - 396195

Report No.	**: 100-240723-3106**
Report Date	: 24/07/2024
Sample Received on	: 23/07/2024
Analysis Date	: 23/07/2024 to 24/07/2024
Report Prepared on	: 24/07/2024
Sampled By	: Customer

Sample Description : Copper Bonded Rod (Dia-17.2mm & Length-3mtr) 250 micron coating.
Condition of the sample on receipt : Received in good condition

Parameter	Unit	Test Method	Result	Requirements as per IEC:62561-2:2012(E)
Physical Analysis				
Bend Test	-	IEC 62561-2:2012(E)	No any crack and peel of Coating observed.	Shall show no sharp edge cracks or peeling.
Ultimate Tensile Strength	Mpa	ISO 6892-1:2009	681.0	600 - 770

Remark:- Sample meets the requirement as per specified limits laid down in IEC:62561-2:2012(E) as observed for the above test parameters only.

*******End of Report*******

Note:

- *This Test report conforms to above test parameters only submitted for testing.*
- *Decision Rule applied- Yes/No UM ±*
- *The sample description is not verified in all cases and is given as described by the customer.*
- *Samples not drawn by us and the analysis conducted as received basis unless specified otherwise.*
- *Tested sample will be disposed off after 30 days from the date of issue of test report unless until specified by customer.*
- *Complaints about this report should be communicated in writing within seven days of issue date of this report.*
- *This report is not to be reproduced wholly or in part and cannot be used as an evidence in the Court of law and shall not be used in the advertising media without our prior permission from the Director.*
- *Laboratory shall maintain the confidentiality of all information related to the samples & Test Reports.*

Ghaziabad Testing Laboratories Pvt. Ltd. Tech. Manager
Auth. Signatory